



1675, HAGGERTY
DRUMMONDVILLE, QC
Telephone: (819) 478-8408
Fax: (819) 478-0199

TECHNICAL DATA SHEET
100113RCAN3E

Cancels & replaces
090120CAN1E

PRO PLASTIC CEMENT

(For dry or damp surface)

Description: *RESISTOSEAL PRO PLASTIC CEMENT* is an all-purpose black mastic composed of bitumen, fibres, mineral fillers and a low level of solvent. It is used for caulking and repairing holes and cracks, it adheres to most materials without primer. Its formulation offers a good resistance to temperature variations.

Application conditions:

- Application temperature range: 0 °C to 35 °C (32 °F to 95 °F).
- In-Service temperature range: -40 °C to 80 °C (-40 °F to 176 °F).
- Can be applied to dry or damp surfaces.

Packaging:

- 310 ml (10 oz) or 850 ml (28 oz) cartridges
- 1 kg, 4 kg, 10 kg & 20 kg pails

Properties:

The *PRO PLASTIC CEMENT* meets or exceeds the requirements of CAN/CGSB-37.5M standard.

Properties	PRO PLASTIC CEMENT	
Colour	Black	
Specific gravity at 22 °C (72 °F)	1.18 kg/L	9.8 lbs/US gal
Solids by Weight	84%	
Flow	None at these temperatures	
Cure time	Between 4 and 24hours depending on temperature and width of applied material	

(All values are nominal)

General instructions: Apply *RESISTOSEAL PRO PLASTIC CEMENT* to clean surfaces. Use the 310 ml (10 oz) cartridges with a standard caulking gun. Do not apply beads wider than 1 cm (3/8 in).

Precautions: *RESISTOSEAL PRO PLASTIC CEMENT* is a flammable product. Store away from open flame. Keep ignition sources away during application and until solvent has evaporated. Do not pour residues in drains. **Consult the Material Safety Data Sheet for more details.**

Storage:

- Maximum storage temperature: 40 °C (104 °F).
- Can support storage temperatures below 0 °C (32 °F).
- Storage conditions: 2 years in its original packaging.

Store in a cool, well-ventilated place.

NOTE: **RESISTO** may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.