

## H<sub>2</sub>O PRIMER

### Interior or Exterior polymeric emulsion-based primer

**Description:** *H<sub>2</sub>O PRIMER* is a polymer emulsion-based primer designed to improve the adhesion of self-adhesive waterproofing membranes on most substrates. Particularly recommended when the use of solvent-based primer is not advised.

**Application:** The substrate must be clean, dry and free of dust, grease or other contaminant.  
*H<sub>2</sub>O PRIMER* may be applied with a paint brush, roller or sprayer on concrete, wood or polystyrene surfaces as well as on gypsum plasterboard.

Average coverage: 0.1 to 0.3 L/m<sup>2</sup> (0.25 to 0.75 US gal/100 ft<sup>2</sup>).

Spraying equipment recommendations:

- Spray tip size: between 20 and 25 mil
- Pressure: 1300 psi continuous

Membranes must be installed on the same day as the application of *H<sub>2</sub>O PRIMER*.

Minimum application temperature: -4 °C (25 °F)

The product must be at minimum 10 °C (50 °F) at the time of application.

**Limitation:** Not suitable for plastic surfaces such as vinyl siding, metal surfaces or water repellent-treated panels.

Do not use to seal self-adhesive membrane joints, as a primer between two membranes or on asphaltic boards (*RESISTOBOARD*).

### Properties:

Properties	<i>H<sub>2</sub>O PRIMER</i>
Specific gravity at 20 °C (kg/L)	1.00
Solids by Weight (%)	55
Colour	Blue
Viscosity (cP)	500
Drying time	30 minutes to 3 hours

(All values are nominal)

**Packaging:** 3.78 L and 18.9 L pails  
Shelf life: Up to 18 months in original sealed containers.

**KEEP FROM FREEZING.**

**Cleaning:** Uncured material can be cleaned with water. Cured material is best removed by solvents such as mineral spirits, varsol, xylene, etc.

**Precautions:** Keep out of reach of children. Harmful if inhaled, swallowed or when in contact with the skin. Do not pour residues in drains.

**CONSULT THE MSDS PRIOR TO USE.**



**NOTE:** RESISTO may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.